



LAMINATED FRONTLIT		
CARACTERISTICI	DATA	METODA de TESTARE
Greutate	440gsm	ISO3801:1977
Tesatura	1000x1000 denier 9x9 fd / inch	DIN60001/DIN EN ISO2060
Tipul coatingului	PVC	N/A
Rezistenta la tractiune	1275N/5cm (L)	ISO527/3:1995
	1101N/5cm (W)	
Rezistenta la rupere	220N/5cm (L)	ISO4674/1:2003
	160N/5cm (W)	
Rezistenta la lipire	CANNOT	DIN53357:1982
Rezistenta la temperaturi scazute	-22°F / -30°C	ISO13934-1:1999
<b>RF Weldable (Heat Sealable)</b>	YES	DIN53354
<b>APLICATII:</b>	Banere, Unipol, Billboar, Sisteme de expnere	
<b>COMPATIBILITARE CERNEALA:</b>	UV, Latex, Solvent, Eco-Solvent, Screen Printing	

